



CHARACTERIZATION AND SOLUBLE PROPERTIES OF NANOMEDICINE SYNTHESIZED FROM PADINA GYMNOSPHORA

Thamizharasan S*

Department of Zoology, Periyar E.V.R College (Affiliated with Bharathidasan University),
Thiruchirappalli-620023, Tamilnadu, India

ARTICLE INFO

Article History:

Received 26th March, 2017
Received in revised form 13th
April, 2017
Accepted 9th May, 2017
Published online 28th June, 2017

Key words:

Ball Milling, Nanoparticles,
Nanosization, Biomaterial

ABSTRACT

Objective: To evaluate the solubility enhancement of plant derived drugs in the form of nonosized biomaterials.

Methods: Nanosization obtained from biomaterial sample of marine macro alga *Padina gymnosphora*, using high energy ball milling technique and structural characteristic studies of biomaterials were evaluated using FE-SEM microscope. Solubility enhancement study on both biomaterials were tested using deionized double distilled water.

Results: FE-SEM microscopic study showed the particle size differentiation in the ordinary crude biomaterial and nanosized biomaterial. Water solubility studies proved the quick soluble and polydispersibility behaviour of nanosized biomaterial.

Conclusion: The solubility enhancement properties of nanosized biomaterials indicated, that when grain or particle size is reduced the solubility is enhanced.

Copyright © 2017 Thamizharasan S. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

INTRODUCTION

According to the World Health Organization, most populations still rely on traditional medicines for their psychological and physical health requirements. People living in rural areas from their personal experience know that these traditional remedies are valuable source of natural products to maintain human health, but they may not understand the science behind these medicines, but knew that some medicinal plants as herbal medicines are highly effective only when used at therapeutic doses [2,6,8]. Herbal medicines in the form of biomaterials are in great demand in both developed and developing countries. Plants produce a diverse range of biomaterials consists of potent bioactive molecules [12, 17]. They making them rich source of different types of medicines. Most of the drugs today are obtained from natural sources or semi synthetic derivatives of natural products and used in the traditional systems of medicine [10, 24,30]. Most of the herbal drug the challenging problems in formulating the drugs are mainly due to the poor solubility is associated to poor dissolution characteristics and thus to poor oral bioavailability [5,27]. It is because of the reason of bulk grain size of biomaterials. Due to the bigger grain size the biomaterial based pharmaceutical drugs could not well soluble [15,31]. Most of the biomaterial incorporated drugs have the properties such as poor solubility, low dispersible nature and poor bioavailability [9]. Hence, the main aim of this study was to produce plant drugs in the form of

nanosized biomaterials by a high energy ball milling technique. It is a novel technique for improving biomaterial based drug and enhancement of its solubility [23,28].

METHODS

Sample Biomaterial

Marine algae *Padina gymnosphora* are the excellent source of bioactive compounds such as carotenoids, dietary fibre, protein, essential fatty acids, vitamins and minerals. This algae have the antimicrobial, antiviral and antifungal activity. It is used in biopharmaceutical industries to produce antimicrobial drugs. In order to enhance the drug characteristics, formulation of bioactive materials of *Padina gymnosphora* in nanomaterial form using High Energy Ball Milling as a novel Nanocrystallization technology.

Sample Collection

Marine algae *Padina gymnosphora* Sample was collected from the sea coast of Rameshwaram, Tamil Nadu, India. Samples were cleaned, epiphytes and necrotic parts were removed. Samples were rinsed with sterile water to remove any associated debris. Sample was kept under sunshade for 7 days. After drying the sample, it was ground thoroughly to powder form using manual mill Shimadzu Blender [4]. After the removal of fibrous and unwanted coarse particle, 100gm of

crude biomaterial powder was taken for the nanosization of the biomaterial using high energy ball milling.

High Energy Ball milling

The crude powder form of biomaterials(w/w) weighed 100gm was milled in steel cells (250 mL) using hardened steel balls (diameter 15 mm, weight 32 gm) in ambient atmosphere for constant time of 15 hours (Retsch, PM 400). The milled materials were used directly without any added milling media. Five balls were kept in each cell along with 100 g of the sample powder. Two parallel cells were used in this experiment (the total weight of the sample powder was 20 g). The synthesized biomaterials were characterized by and the morphology of the powders was analyzed using a field emission scanning electron microscope (FESEM), JSM-7500 F (JEOL-Japan) operated at 10 KV, in the Centre for Nanoscience and Technology, Bharathiar University, Coimbatore, Tamilnadu, India.

Experimental Design

To find out the highly potent water solubility of biomaterials(drugs), synthesized from the marine macro algae *Padina gymnosphora*, we have taken two types of algal biomaterial in the form of powder, 1.Crude biomaterial produced by manual mill Shimadzu Blender and 2. Nanosized biomaterial using high energy ball milling. Both the two powder samples were tested to observe the solubility.

RESULTS

Structural and Morphological Studies Figure 1(A) shows FESEM micrograph image of the starting biomaterial sample before ball milling process. This sample contains particles covering the range 12-30 μm of different sizes/shapes. Around 70% of these particles are large and irregular shape. The ordinary powder form (crude biomaterial) produced by

ordinary manual mill Shimadzu Blender may lead to formation of large irregular size and shape. Figure 1 (B) indicates FESEM micrograph image of the biomaterial sample milled for about 15 hours by High Energy Ball milling device. The images of the biomaterial sample milled for 15 hours, show particles of nano size, almost all particles are semi spherical shaped nanoparticles. The particle size distributions for the sample with more collected particles have an average diameter of approximately 90 to 140 nm

Solubility Enhancement Studies

The water solubility or aqueous solubility of crude algal biomaterial of the particles size (12-30 μm) and High energy ball milled algal biomaterial of the particle size (90 to 140 nm) shows differentiation. The crude biomaterial sample added into Deionized double distilled water partially soluble and partially dispersible and a lot of green depositions appeared in the solution. The solution shows acidic pH value 5.0.

While in the nanosized sample, the particle solubility rate and dispersion efficiency is very high. The nanosized sample was quickly soluble in water and the pH value reached as 6.5 to 7.0. Further it was observed in the solution indicated mild brownish colour with uniform solubility and dispersibility properties.

DISCUSSION

High Energy Ball milling is a powerful non-equilibrium processing method capable of producing dispersion strengthened materials and alloys with fine microstructures as well as metastable nanostructured materials [1]. The milling process, which can be either mechanical milling or mechanical alloying, refines the grain size of all solid elements of materials into nanoscale [14].

During the ball milling process, algal biomaterials are repeatedly fractured, and nanosized. Fracture and nanosize are the two basic factors that produce a permanent ionic exchange between particles. Ball milling technology leads to an increase in dissolution rate depending on the increase in surface area obtained by reduction of the particle size of the active drug substance down to the nano size range preserving the crystal morphology of the drug biomaterial [21,32]. A number of researchers have produced nanosized materials using the same technology [7,18].

This technology leads to an increase in dissolution rate depending on the increase in surface area obtained by reduction of the particle size of the active drug substance down to the nano size range preserving the crystal morphology of the drug. [11,13]. The milling process, which can be either mechanical milling or mechanical alloying, refines the grain size of all solid elements of materials into nanoscale [3,19]. The minimum grain size can be obtained by a balance between the defect introduced by plastic deformation of milling and its recovery by thermal cases. The orientation of the grain becomes random. The high angle grain boundaries replace the low angle grain boundaries by boundary rotation or sliding. Finally, the grain boundaries near the sample edge are broken and single crystals nanoparticles are peeled off the edge of the samples [25]. The main advantages of ball milling include large scale production of high purity nanoparticles with improved physical properties in a cost effective way [22,29]. The ball milling treatments can also bring new properties to the matter depending on the grain size and materials




Fig 1A FE-SEM image of the ordinary crude biomaterial prepared by manual mill Shimadzu Blender.




Fig 1B FE-SEM image of the nanosized biomaterial prepared by High Energy Ball Milling.

composition [20]. In our investigation, the ball milling operation may lead to formation of nanosized particles. The ordinary blender produced microsized particles which is larger than the nano particle. This result clearly presents that the ball mills are more effective to reduce size, which ultimately increase the accessibility of particle size to biomaterials and easy solubility. Most differentiating features of drug nanocrystals are the increased saturation solubility and the accelerated dissolution velocity.

The main advantages of ball milling include large scale production of high purity nanoparticles with improved physical properties. in a cost effective way [26,33].The ball milling treatments can also bring new properties to the matter depending on the grain size and biomaterials composition including its solubility.

CONCLUSIONS

The present study proves remarkable experimental results on algal biomaterial using High energy ball milling processes for the controlled synthesis of drug nanoparticles found in the algal biomaterial were described. The ball milling process are successfully produced the nanoparticles in biomaterial with high solubilization capacity. The size reduction of algal biomaterial to nanometer levels (from 60-120 nm) has been achieved by this method on 15 h. This technology helpful to an increase in dissolution rate of drug biomaterial depending on the increase in surface area obtained by reduction of the particle size of the active drug substance down to the nanosize. Ball milling technology can be used to formulate and improve drugs and its compounds activity and enhance the solubility of the poorly water-soluble compounds.

Acknowledgement

Authors would like to acknowledge sophisticated analytical instrumental facility in NIT-Tiruchirappalli, and Centre for Nanoscience and Technology, Bharathiar University, Coimbatore, Tamilnadu, India. For providing FE-SEM and High Energy Ball Milling facilities for the experiments.

References

- Lipinski, C. (2002) Poor aqueous solubility-an industry wide problem in drug discovery. *Am. Pharm. Rev.* 5, 82-85
- Heimbach, T. et al. (2007) Overcoming poor aqueous solubility of drugs for oral delivery. In Prodrugs. pp. 157-215
- Serajuddin, A.T. (2007) Salt formation to improve drug solubility. *Adv. Drug Delivery Rev.* 59, 603-616
- Strickley, R.G. (2004) Solubilizing excipients in oral and injectable formulations. *Pharm. Res.* 21, 201-230
- Junghanns, J.-U.A.H. and Muller, R.H. (2008) Nanocrystal technology, drug delivery and clinical applications. *Int. J. Nanomed.* 3, 295-309
- Marcato, P.D. and Duran, N. (2008) New aspects of nanopharmaceutical delivery systems. *J. Nanosci. Nanotechnol.* 8, 2216-2229
- Riehemann, K. et al. (2009) Nanomedicine - challenge and perspectives. *Angew. Chem. Int. Ed. Engl.* 48, 872-897
- Noyes, A.A. and Whitney, W.R. (1897) The rate of solution of solid substances in their own solutions. *J. Am. Chem. Soc.* 19, 930-934
- Van Eerdenbrugh, B. et al. (2008) Top-down production of drug nanocrystals: nanosuspension stabilization, miniaturization and transformation into solid products. *Int. J. Pharm.* 364, 64-75
- Chen, H.B. et al. (2008) A facile nanoaggregation strategy for oral delivery of hydrophobic drugs by utilizing acid-base neutralization reactions. *Nanotechnology* 19, 375104
- Gao, L. et al. (2008) Drug nanocrystals for the formulation of poorly soluble drugs and its application as a potential drug delivery system. *J. Nanopart. Res.* 10, 845-862
- Chen, J.-F. et al. (2004) Feasibility of preparing nanodrugs by high-gravity reactive precipitation. *Int. J. Pharm.* 269, 267-274
- Merisko-Liversidge, E. et al. (2003) Nanosizing: a formulation approach for poorlywater- soluble compounds. *Eur.J. Pharm. Sci.* 18, 113-120
- Hecq, J. et al. (2005) Preparation and characterization of nanocrystals for solubility and dissolution rate enhancement of nifedipine. *Int. J. Pharm.* 299, 167-177
- Lipinski C, Poor aqueous solubility- an industry wide problem in drug discovery, *Am. Pharm. Rev.* 2002; 5: 82-85.
- Keck C, Kobierski S, Mauludin R, Muller RH, (2008), Second generation of drug nanocrystals for delivery of poorly soluble drugs: smartcrystals technology, D O S I S, 24(2):125-127.
- Mosharraf M, Nystrom C, (1995), The effect of particle size and shape on the surface specific dissolution rate of micronized practically insoluble drugs, *Int J Pharm*, 122: 35-47.
- Rawat N, Senthil M, (2011), Solubility: Particle Size Reduction is a Promising Approach to Improve The Bioavailability of Lipophilic Drugs, *International Journal of Recent Advances in Pharmaceutical Research*, 1: 8-18.
- Lipinski C. (2002), Poor aqueous solubility - an industry wide problem in drug delivery. *Am Pharm Rev*: 82-85.
- Suryanarayana,C. *MechanicalAlloying and Milling*; Marcel Dekker:New York, 2004.
- Babu Rao, J.; Catherin, G. J.; Narasimha Murthy, I.; Venkata Rao, D.; NookaRaju, B.
- Production of nano structured silicon carbide byhigh energy ball milling. *Int. J. Eng. Sci. Technol.* 2011, 3(4), 82-88.
- Williamson, K.; Hall, W. H. X-ray line broadening from filed aluminium and wolfram. *Acta Metall.* 1953, 1, 22-31.
- Mohammad Sharifi, E.; Karimzadeh, F.; Enayati,M. H. A study on mechano chemical behavior of B2O3-Al system to produce aluminabased nano composite. *J. Alloys Comp.* 2009, 482, 110-113.
- Shamah, A. M.; Ibrahim, S.; Hanna, F. F. Formation of nano quasicrystalline and crystalline phases by mechanical alloying. *J. Alloys Comp.* 2011, 509, 2198-2202.
- Hwang, Y.; Lee, J. Preparation of TiB₂ powders by mechanical alloying. *Mater. Lett.* 2002, 54, 1-7.
- Haghshenas Jazi, E.; Borhani,G.; Esalmi Farsani, R. Preparation of Al-Fe/TiB₂ nanocomposite powder by

- ball milling and subsequent heat treatment. *Micro Nano Lett.* 2012, 7(5), 448-452.
28. Haghshenas Jazi, E.; Borhani,G.; Esalmi Farsani, R.; Sharifian Jazi, F. Synthesis and characterization of in-situ Al-Al13Fe4-Al2O3-TiB2 nanocomposite powder by mechanical alloying and subsequent heat treatment. *Synth. React. Inorg. Met.-Org. Nano-Met. Chem.* 2013, in press.
29. Sharifian Jazi, F.; Parvin, N.; Rabiei, M.; Tahriri, M.; Moshefi Shabestari, Z.; Azadmehr, A. R. The effect of the synthesis route on the grain size and morphology of ZnO/Ag nanocomposite. *J. Ceram. Process. Res.* 2012, 13, 523-526.
30. Thomas Paul, K.; Satpathy, S. K.; Manna, I Jazi, F. S.; Parvin, N.; Azadmehr, A. R.; Tahriri, M. Influence of annealing temperature on distribution and morphology of silver powder in SnO₂-Ag₂O nanocomposite. *Adv. Appl. Ceram.*, in press.
31. Abedini, S.; Parvin, N.; Ashtari, P.; Jazi, F. S. Microstructure, strength and CO₂ separation characteristics of α -alumina supported γ -alumina thin film membrane. *Adv. Appl. Ceram.* 2013, 112, 17-22.
32. Nayaka, S. S.; Wollgartenb, M.; Banhartb, J.; Pabia, S. K.; Murtyc, B. S. Nanocomposites and an extremely hard nanocrystalline intermetallic of Al-Fe alloys prepared by mechanical alloying. *Mater. Sci. Eng. A* 2010, 527, 2370-2378.
33. Sharifi, E. M.; Karimzadeh, F.; Enayati, M. H. Preparation of Al₂O₃-TiB₂ nanocomposite powder by mechanochemical reaction between Al, B₂O₃ and Ti. *Adv. Powder Technol.* 2011, 22, 526-531.
